

## **Technical Data Sheet**

Туре	IRON OXIDE GREEN (835)
Oil absorption (ml/100g)	25-35
Residue on 325 Mesh (%)	≤0.3
Water soluble salts (%)	≤2.0
Moisture(%)	≤1.0
PH Value	6
Specific gravity(g/ml)	5.2
Particle size by BET	0.4-0.8 um
riangleE compared with std	≤1.0
Tinting Strength(%)	95-105