Technical Data Sheet

C.I.Pigment No.	Fast Violet HD-256(P.V.23)
CAS	6358-30-1
C.I.No.	51319
Physical Properties	
Specific Gravity	1.4-1.60
Specific Surface area(m^2/g)	45-102
pH	6-7
Specification	
Color Shade	Similar to the standard
Color Strength	100%± 5
Volatile matter at 105 °C	1.5%max
Soluble matter in water	1.5%max
Moisture	3.0% max
Oil absorption	40-55 ml/100g
Fastness to	
Light	7-8
Heat	200 °C
Bleeding in	
Water	5
Oil	5
Resistance to:	
Acid	5
Alkalis	5
Toluene	5
Xylene	5
Butanol	4-5
Ethyl Glycol	4-5
Butyl Acetate	4-5
MEK	4-5
Mineral Spirits	4-5
Dibutyl Phtalate	4-5

www.Radmarchem.com

地址: 宁波市科技园区清水桥路 535 号新城国际 11 楼
Add: 535 QINGSHUIQIAO ROAD 11TH FLOOR OFFICE PARK BUILDING NINGBO HI-TECH PARK 315040 CHINA
电话(Tel): 0574-87907888 87019204 FAX 87917070 87265831
Http://www.hongda-chem.com
E-mail: chemcolor@hongda-chem.com